

Avstenitno jeklo / Austenitic stainless steel / Austenitischer Stahl

Wr. Nr. (1)	DIN EN (2)	AISI (3)	JUS (4)	UNS (5)	SS (6)	AFNOR (7)	BS (8)
1.4301	X 5 CrNi 18 10	304	Č.4580	S 30400	2332	Z 6 CN 18.09	304 S 15
1.4305	X 8 CrNiS 18 9	303	Č.4590	S 30300	2346	Z 8 CNF 18.09	303 S 13
1.4306	X 2 CrNi 19 11	304 L	Č.45701	S 30403	2352	Z 3 CN 19.09	304 S 11
1.4307	X 2 CrNi 18 9	304 L	Č.45701	-	-	-	-
1.4310	X 10 CrNi 18 8	301	Č.4571	S 30100	2331	Z 12 CN 18.08	301 S 22
1.4401	X 5 CrNiMo 17 12 2	316	Č.4573	S 31600	2347	Z 7 CND 17.11.02	316 S 31
1.4404	X 2 CrNiMo 17 13 2	316 L	Č.45703	S 31603	2348	Z 3 CND 18.11.02	316 S 11
1.4435	X 2 CrNiMo 18 14 3	316 L	Č.45704	S 31603	2353	Z 3 CND 18.14.03	316 S 11
1.4436	X 5 CrNiMo 17 13 3	316	Č.45706	S 31600	2343	Z 7 CND 18.12.03	316 S 31
1.4539	X 1 CrNiMoCuN 25 20 5	-	-	N 08904	2562	Z 2 NCDU 25.20	904 S 13
1.4541	X 6 CrNiTi 18 10	321	Č.4572	S 32100	2337	Z 6 CNT 18.10	321 S 31
1.4571	X 6 CrNiMoTi 17 12 2	316 Ti	Č.4574	S 31635	2350	Z 6 CNDT 17.12	320 S 31
1.4828	X 15 CrNiSi 20 12	309	Č.4577	S 30900	-	Z 17 CNS 20.12	309 S 24
1.4841	X 15 CrNiSi 25 20	314, 310	Č.4578	S 31400	-	Z 15 CNS 25.20	314 S 25
1.4845	X 12 CrNi 25 21	310 S	-	S 31008	2361	Z 8 CN 25.20	310 S 31
1.4878	X 10 CrNiTi 18 10	321 H	-	S 32100	2337	Z 6 CNT 18.12	321 S 51

Duplex / Duplex / Duplex

Wr. Nr. (1)	DIN EN (2)	AISI (3)	JUS (4)	UNS (5)	SS (6)	AFNOR (7)	BS (8)
1.4410	X 2 CrNiMoN 257 4	-	-	-	-	Z 3 CND 25.06 Az	-
1.4462	X 2 CrNiMoN 22 5 3	2205	-	S 31803	2377	Z 3 CND 22.05 Az	318 S 13

Feritno jeklo / Ferritic stainless steel / Ferritischer Stahl

Wr. Nr. (1)	DIN EN (2)	AISI (3)	JUS (4)	UNS (5)	SS (6)	AFNOR (7)	BS (8)
1.4016	X 6 Cr 17	430	Č.4174	S 43000	2320	Z 8 C 17	430 S 17
1.4713	X 10 CrAlSi 7	-	Č.4974	-	-	Z 8 CA 7	-
1.4724	X 10 CrAlSi 13	405	Č.4972	S 40500	-	Z 10 C 13	403 S 17
1.4762	X 10 CrAlSi 25	446	Č.4970	S 44600	2322	Z 10 CAS 24	-

Martenzitno jeklo / Martensitic stainless steel / Martensitischer Stahl

Wr. Nr. (1)	DIN EN (2)	AISI (3)	JUS (4)	UNS (5)	SS (6)	AFNOR (7)	BS (8)
1.4006	X 12 Cr 13	410	Č.41701	S 41000	2302	Z 10 C 13	410 S 21
1.4021	X 20 Cr 13	420 L	Č.4172	S 42010	2303	Z 20 C 13	420 S 29
1.4028	X 30 Cr 13	420 M	Č.4173	S 42000	2304	Z 33 C 13	420 S 37
1.4034	X 46 Cr 13	-	Č.4175, Č.4173	-	-	Z 44 C 14	-
1.4057	X 17 CrNi 16 2	431	Č.4570	S 43100	2321	Z 15 CN 16.02	431 S 29
1.4104	X 12 CrMoS 17	430 F	Č.4790	S 43020	2383	Z 13 CF 17	-
1.4112	X 90 CrMoV 18	440 B	Č.4772	S 44003	-	-	-
1.4122	X 39 CrMo 17 1	-	Č.4772	-	-	Z 38 CD 16.01	-

- (1) Werkstoff Number
- (2) Deutsches Institut für Normung
- (3) American Iron and Steel Institute
- (4) Jugoslovanski zavod za standardizacijo, Jugoslovanski standardi
- (5) Unified Numbering System
- (6) Swedish Standard
- (7) Association française de Normalisation
- (8) British Standard